



NPK PLUS



DESCRIPTION: A PROFESSIONAL 8 TO 9 MONTH ◊ CONTROLLED RELEASE NURSERY FERTILIZER SPECIFICALLY FORMULATED TO MEET THE NUTRITIONAL NEEDS OF CONTAINER GROWN TREES AND SHRUBS.

BENEFITS:

- APEX® NPK PLUS provides the improved safety of POLYON® Reactive Layers Coating (RLC) controlled release technology.
- Release of nutrients with POLYON® is predictable and reliable. The coating has been precisely applied to ensure the safety and effectiveness of each granule.
- Release of nutrients is not significantly affected by media type, moisture level, pH, or microbial activity.

Soil / Media Temperature Release Rates

- 10.0° C 11-12 Months
- 15.5° C 8-10 Months
- 21.0° C 8-9 Months ◊
- 26.5° C 6-7 Months

APEX 22-2.6-6.6 NPK PLUS

GUARANTEED ELEMENTAL ANALYSIS:

TOTAL NITROGEN (N)**	22.00%
6.50% Ammoniacal Nitrogen	
5.50% Nitrate Nitrogen	
10.00% Urea Nitrogen	
TOTAL PHOSPHORUS (P)**	2.60%
TOTAL POTASSIUM (K)**	6.60%
Magnesium (Mg)	0.50%
Sulphur (S)**	3.00%
Copper (Cu)	0.05%
Iron (Fe)	0.20%
Manganese (Mn)	0.05%
Molybdenum (Mo)	0.0006%
Zinc (Zn)	0.05%

Derived from Polymer-Coated Urea, Polymer-Coated Ammonium Nitrate, Polymer-Coated Ammonium Phosphate, Polymer-Coated Sulphate of Potash, Magnesium Carbonate, Magnesium Oxide, Magnesium Sulphate, Copper Oxide, Copper Sulphate, Ferrous Sulphate, Manganese Oxide, Manganese Sulphate, Sodium Molybdate, Zinc Oxide and Zinc Sulphate.

POLYON® is a registered trademark owned by Agrium and used under license.

**A portion of the nitrogen, phosphorus, potassium and sulphur materials in this product have been coated to provide 22.00% coated slow release nitrogen (N), 2.60% coated slow release total phosphorus (P), 6.60% coated slow release total potassium (K) and 2.60% coated slow release sulphur (S).

APPLICATION RATES:

Use LOW rate for low feeding, sensitive plants or under high soil temperatures.

Use MEDIUM rate for medium to moderately heavy feeding plants.

Use HIGH rate only for heavy feeding hardy plants.

These application rates are based on the average temperature at the fertilizer location of 21.0°C.

Increase fertilizer application rates by 20% if average monthly temperatures are lower than 15.5°C.

Lower application rates by 20% if average monthly temperatures are greater than 26.5°C.

TOPDRESS CONTAINER: Plant Nutrient Requirements / Uniformly apply (topdress) product onto the container surface using the amounts listed below:

DIAMETER (mm)	LOW	MEDIUM	HIGH
100mm	1.2 grams	1.8 grams	2.4 grams
125mm	2.4 grams	3.7 grams	5.0 grams
150mm	4.0 grams	6.0 grams	8.0 grams
175mm	7.0 grams	11.0 grams	15.0 grams
200mm	10.0 grams	16.0 grams	22.0 grams
250mm	20.0 grams	35.0 grams	50.0 grams
300mm	30.0 grams	50.0 grams	70.0 grams

INCORPORATION: Plant Nutrient Requirements / Uniformly mixed (incorporated) nursery fertilizer into potting media as follows:

Kilograms per cubic metre	LOW 3.5kg	MEDIUM 5.5 kg	HIGH 7.5kg
---------------------------	-----------	---------------	------------

PLANTING BED: Plant Nutrient Requirements (incorporate if possible or use lower rates) as follows:

Kilograms per 100 square metres	LOW 10kg	MEDIUM 20 kg	HIGH 30kg
---------------------------------	----------	--------------	-----------

APPLICATION PRECAUTIONS:

- Trial before use of this product under your local growing conditions, application methods, and desired rates. Avoid application to plants under stress.
- If mixed media is not used within 1 week, leach thoroughly before using.
- Product left in media for more than 1 week will lose longevity resulting in reduced release time and wasted controlled release fertilizer.
- Avoid the use of media processing equipment that could change the integrity of Reactive Layer Coated.
- Avoid mounding of fertilizer against base of the plant.
- Iron and other plant nutrients can cause staining of cement.
- Keep away from pools, ponds and other bodies of water.
- When using potting media with higher cation exchange capacities use lower recommended rates of this formulation.
- When using supplemental liquid feed reduce the rate of this formulation accordingly.
- Do not incorporate into media prior to steam sterilisation.
- This product is not recommended for dibble applications.
- To avoid the build up of soluble salts, occasional leaching may be necessary.